

NASSIMI

Nassimi LLC T 212.643.8080
370 Seventh Avenue T 800.521.5208
Suite 1600 F 212.643.2626
New York, NY 10001 W www.nassimi.com

Product Specification Sheet

Pattern: Baron

Date: 07/12/2011

ENCORE by The Symphony Collection

General Specifications

Weight (linear yard)	19.0 oz
Width	54 "
Thickness	0.80 mm
Gauge	N/A
Emboss	Paper
Surface Composition	100% Polyurethane
Substrate Composition	100% Polyester
Substrate Weight	6.5 oz

General Treatments

Hydrolysis Resistance	7 yrs	ISO 1419:1995 (Jungle Test)
UV Resistance	200 Hours	CFFA-2 / ASTM G26-96 Method C
Cold Crack	-20 F	CFFA-6 Federal Standard No. 191A-Method 5874
Mildew Resistant	Pass	CFFA-120 / ASTM G21-96
Anti-Bacterial	Pass	CFFA-300 / AATCC* Test Method 147-1998
Anti-Microbial	Pass	CFFA-300 / AATCC* Test Method 147-1998
Cleangene Technology	Yes	
Bleach Resistant	Yes	Diluted 3:1

Physical Strength Properties

Abrasion	300,000+ Cycles		CFFA-1A/ Method ASTM D 4157-92
Adhesion	8.93 Warp	10 Fill	CFFA 3/ ASTM D751-98
Tear Strength	9.3 Warp	12.8 Fill	CFFA-16/ ASTM D2261-96
Breaking Strength	147 Warp	73 Fill	CFFA-17/ ASTM D751-00
Seam Strength	56 Warp	41.9 Fill	CFFA-14/ Method ASTM D751-98
Blocking Resistance	2 Rating		CFFA-4/FTMS 191A-TM5872
Crocking	4.5 Dry	4.5 Wet	AATCC-Method 8-2001

Flame Retardancy Standards

California Technical Bulletin 117	Pass	Boston Fire Code (BFD IX-1)	N/A
UFAC Class I	Pass	IMO A.652(16)8.2	Pass
BIFMA CS-191-53, Section 3	Pass	ASTM E84: Class I	Pass
BIFMA Upholstery, Section 4	Pass		
NFPA 260	Pass		