

NASSIMI

Nassimi LLC T 212.643.8080
370 Seventh Avenue T 800.521.5208
Suite 1600 F 212.643.2626
New York, NY 10001 W www.nassimi.com

Product Specification Sheet

Pattern: Bondi

Date: 06/ 21/ 2011

team performance

General Specifications

Weight (linear yard)	32 oz
Width	54 "
Thickness	1.0 mm
Surface Composition	PVC
Substrate Composition	100% Polyester
Substrate Weight	3.75 oz

General Treatments

UV Resistance	1,000 Hours	CFFA-2 / ASTM G26-96 Method C
Cold Crack	-20 F	CFFA-6 Federal Standard No. 191A-Method 5874
Mildew Resistant	Pass	CFFA-120 / ASTM G21-96

Physical Strength Properties

Abrasion	300,000+ Cycles	CFFA-1A/ Method ASTM D 4157-92
Tear Strength	25.8 Warp 27.7 Fill	FTM 5136
Break Strength	89.2 Warp 102.7 Fill	FTM 5100.1

Flame Retardancy Standards

California Technical Bulletin 117	Pass	NFPA 260	Pass
UFAC Class I	Pass	IMO A.652(16)8.2	Pass
BIFMA CS-191-53, Section 3	Pass	IMO A.652(16)8.3	Pass
BIFMA Upholstery, Section 4	Pass		
MVSS 302	Pass		